

Technical Specifications

Spécifications techniques - Technische specificaties - Technische Spezifikationen

Adhesive carrier Support adhésif - zelfklevende drager - Klebender Träger		Selfwound, Linerfree system
Adhesive system Système adhésif - Lijmsysteem - Klebesystem		Acrylic dispersion
Liner Doublure - Voering - Futter		Transparent polyester film
Thickness (without liner) Épaisseur (sans doublure) - Dikte (zonder voering) - Dicke (ohne Futter)	ASTM D3652	0,215 mm
Peel Adhesion EcoFlex™ Statera Adhérence - Hechting - Haftfestigkeit	ASTM D- 1002	320 N/Meter
Peel Adhesion EcoFlex™ Echo Adhérence - Hechting - Haftfestigkeit	ASTM D- 1002	420 N/Meter
Recommended processing temperature Température de traitement recommandée - Aanbevolen verwerkingstemperatuur - Empfohlene Verarbeitungstemperatur		+ 10 °C tot +30°C
Temperature resistance Résistance à la température - Temperatuurbestendigheid - Temperaturbeständigkeit		40 °C tot +140°C
Aging resistance Comportement au vieillissement - Verouderingsbestendigheid - Alterungsbeständigkeit		Very high
Plasticizer resistance Résistance au plastifiant - Weekmaker weerstand - Weichmacherbeständigkeit		Very high

We reserve all rights for technical improvements. 03/2024

Application Techniques

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance